

PACKAGING




MIXING



APPLICATION



USES



SUBSTRATES

ALL TILED AREAS

As a PRIMER - for Dusty & Porous Masonry Surfaces

As a GROUT ADDITIVE - Improves Flexural Strength, Mould Resistance & Reduces Staining

PRIMER

DESCRIPTION

An acrylic based liquid used to eliminate the possibility of adhesion failure on dusty and porous surfaces. Use on building boards, concrete, cement render and gypsum building boards.

APPLICATION

Ready to Use. Do not dilute. Apply with a roller, brush or sponge and allow to dry for approximately 15 minutes. Do not use on continuously damp surfaces.

COVERAGE (Approximate) 8m²/litre.

GROUT ADDITIVE

DESCRIPTION

An acrylic based liquid additive for Kemgrout to increase the strength, mould resistance and reduce grout staining and discolouration. **Changes the colour of the grout to the next darker shade.**

APPLICATION

Dilute 50:50 with water. Mix with Kemgrout to a thick, creamy consistency and apply as per directions on Kemgrout bag.

COVERAGE (Approximate)

2-3 Litres per 20kg of Grout.

PERFORMANCE DATA

PRIMER - shear bond adhesion kg/cm ²			
	No Bond Coat	PVA Primer	Grout
7 day	2.25	6.26	26.65
28 day	2.25	6.54	35.72
7 day dry/7 day wet	6.26	7.45	20.04

GROUT ADDITIVE - shear bond adhesion kg/cm ²		
	3:1 Mortar	Primer Grout Additive in 3:1 Mortar
Dry	1.02	40.8
Wet	3.06	17.34

SPECIFICATION

The Primer/Grout and Additive will be a water based acrylic and shall have a shear bond strength as a primer of 35.72 kg/cm² and an adhesion to concrete of 4N/mm² as an additive such as Primer & Grout Additive manufactured by Construction Chemicals and shall be applied in accordance with the manufacturers application instructions.

SHELF LIFE 1 year

**CONSTRUCTION
CHEMICALS**

- **ADELAIDE** 467 - 469 SOUTH RD REGENCY PARK 5010 PH: (08) 8346 8013 FAX: (08) 8340 2052
- **BRISBANE** 45 COULSON ST WACOL 4076 PH: (07) 3271 2944 FAX: (07) 3271 3892
- **MELBOURNE** 1 / 10 GABRIELLE CT BAYSWATER NORTH 3153 PH: (03) 9761 4711 FAX: (03) 9761 4748
- **PERTH** 61 DOWD ST WELSHPOOL 6106 PH: (08) 9358 6493 FAX: (08) 9358 6493
- **SYDNEY** 2/ 31-33 NEWTON RD WETHERILL PARK 2164 PH: (02) 9756 3533 FAX: (02) 9756 3534
- **AUCKLAND** 16 CARPENTER RD EAST TAMAKI PH: (09) 273 5444 FAX: 0800 266 236
- **KUALA LUMPUR** LOT 2 JALAN KECAPI 33/2 ELITE INDUSTRIAL ESTATE OFF JALAN BUKIT KEMUNING PH: (03) 552 2522 FAX: (03) 522 2526

"The information contained in this technical publication is based on our current knowledge and experience and is provided as a guide only. In view of the many factors that may affect application it is the users sole responsibility to ensure suitability for a specific purpose."